

P21086.A02

27. Nickel based-alloy according to claim 8, comprising at least one element of Group 3 of the periodic table, except actinoids, said at least one element being present up to 0.15 wt-%; and comprising manganese (Mn), said Mn being present up to 0.60 wt-%.

28. Nickel based-alloy according to claim 8, comprising at least one element of Group 3 of the periodic table, except actinoids, said at least one element being present up to 0.15 wt-%; and comprising iron (Fe), said Fe being present up to 14.8 wt-%.

29. Nickel based-alloy according to claim 8, comprising at least one element of Group 3 of the periodic table, except actinoids, said at least one element being present up to 0.15 wt-%; and comprising boron (B), said B being present up to 0.01 wt-%.

30. Nickel based-alloy according to claim 8, comprising manganese (Mn), said Mn being present up to 0.60 wt-%; and comprising iron (Fe), said Fe being present up to 14.8 wt-%.

31. Nickel based-alloy according to claim 8, comprising manganese (Mn), said Mn being present up to 0.60 wt-%; and comprising boron (B), said B being present up to 0.01 wt-%.

32. Nickel based-alloy according to claim 8, comprising iron (Fe), said Fe being present up to 14.8 wt-%; and comprising boron (B), said B being present up to 0.01 wt-%.

#### REMARKS

Entry of the amendment herein is requested prior to examination of the application.

The amendments herein are being presented to even more clearly disclose Applicants' invention by even more clearly defining that the nickel-based alloy comprises a minimum of 51 wt-% of nickel (Ni) or a combination of nickel (Ni) and cobalt (Co).

P21086.A02


Moreover, the specification has been corrected to denote, when referring to the nickel-based alloy of DE-C-4411228, that it contains 0.10 to 3.0 silicon as compared to nitrogen. This change does not constitute new matter because it is merely including the subject matter disclosed in this document, as can be seen from a copy of the document submitted with the Information Disclosure Statement submitted on even date herewith.

Still further, it is noted that the claims have been amended by canceling original presented claims 1-7, and adding claims 8-32, to remove multiple dependent claims, and to place the claims more in accordance with idiomatic English and standard U.S. practice. For example the recitations in claim 1 relating to amounts of alloying components that can be present up to the recited amounts have been placed into dependent claims. Also, the amended claim have been placed into the Summary of the Invention section of the specification.

Applicants note that the amendments which have been made in this amendment should be considered to have been made for a purpose unrelated to patentability, and no estoppel should be deemed attached thereto.

If there should be any questions, the Examiner is invited to contact the undersigned at the telephone number listed below.

Respectfully submitted,  
Markus SPEIDEL et al.

 Reg. No. 33,094  
Neil F. Greenblum  
Reg. No. 28,394

September 14, 2001  
GREENBLUM & BERNSTEIN, P.L.C.  
1941 Roland Clarke Place  
Reston, VA 20191  
(703) 716-1191

Nickel-Based Alloy for High-Temperature TechnologyBACKGROUND OF THE INVENTION**1. Field of the Invention**

[0001] The present invention relates to a creep-proof and corrosion-resistant nickel-based alloy for use in high-temperature technology.

**2. Discussion of Background Information**

[0002] Increasingly, higher mechanical and corrosion chemical demands are placed on metal materials at operational temperatures of more than 900°C, in particular for hot work tools, for components of gas turbines and motors, for elements in oven construction, and in chemical industries. Due to corrosion wear and also in view of the toughness and the creep characteristics of the material, nickel-based alloys containing chromium are well-suited for use at very high temperatures.

[0003] A nickel-based alloy with the abbreviation NiCr 7030 according to the DIN material number 2.4658 is considered heat-resistant and is used for heat conductors, oven components, and the like. Although such a material has good oxidation resistance, depending on its silicon and aluminum content, it is also provided with a low toughness and low time yield as well as high creep values at operational temperatures of approximately 1000°C.

[0004] A nickel-based alloy that is resistant to high temperatures is known from DE-C-4411228. This high-temperature-resistant, oxidation-resistant, massively nitrophenated, hot and cold formable nickel-based alloy is essentially composed of (in mass-%) 0.001 to 0.15 carbon, 0.10 to 3.0 [nitrogen] silicon, 25.0 to 30.0 chromium, more than 0.3 to 1.2 nitrogen, 0.001 to 0.01 boron, 0.01 to 0.5 yttrium, cerium, lanthanum, hafnium, and tantalum, [separate] alone or in combination, the remainder being nickel with a content of at least 64.0 %. Although a mixed crystal hardening can be achieved due to the carbon content, the primarily effective elements of the above-mentioned alloy with regard to the high-temperature characteristics are chromium and nitrogen. Chromium and nitrogen form



#8

chromium nitrides which improves creep characteristics, with nitrogen additionally providing a mixed crystal hardening. Considerably improved creep characteristics and heat resistance values seem achievable using the alloy according to DE-C-441 1228.

[0005] In the temperature range between 900°C and 1200°C, a so-called creeping of the material during stress and a worsening of corrosion resistance occurs, in particular during cyclic wear, in conventional nickel-based materials, which are exposed to higher wear to an increasing extent. The object of the present invention is to remove these shortcomings and to create an improved nickel-based alloy for high-temperature use.

### **SUMMARY OF THE INVENTION**

[0006] [This] The object according to the present invention is attained in a creep-proof and corrosion-resistant nickel-based alloy comprising in wt-%:

0.0015 to 0.60 carbon (C)

0.20 to 0.90 nitrogen (N)

22.0 to 32.0 chromium (Cr)

5.0 to 20.0 elements of group 4, 5, and 6 of the periodic table, except Cr

0.03 to 3.0 aluminum (Al)

0.4 to 3.0 silicon (Si)

up to 0.15 elements of group 3 of the periodic table, except actinoids

up to 0.60 manganese (Mn)

up to 14.8 iron (Fe)

up to 0.01 boron (B)

a maximum of 0.014 phosphorus (P)

a maximum of 0.004 sulfur (S)

a minimum of 51 nickel (Ni) [and/or] or a combination of nickel (Ni) and

cobalt (Co)

and melting-related impurities.

[0007] Thus, the present invention is directed to a creep-proof and corrosion-resistant nickel-based alloy for the use in high-temperature technology comprising, in wt-%:

0.0015 to 0.60 carbon (C);

0.20 to 0.90 nitrogen (N);

22.0 to 32.0 chromium (Cr);

5.0 to 20.0 elements of the groups 4, 5, and 6 of the periodic table, except

Cr;

0.03 to 3.0 aluminum (Al);

0.4 to 3.0 silicon (Si);

maximum of 0.014 phosphorus (P);

maximum of 0.004 sulfur (S);

minimum of 51 of nickel (Ni) or a combination of nickel (Ni) and cobalt

(Co); and

melting-related contaminants.

[0008] The carbon can be present in 0.16 to 0.5 wt-%.

[0009] The ratio of nitrogen to carbon can be 0.5 to 5.5, preferably 1 to 4, and optionally 1 to 3.

[0010] The nickel-based alloy can contain a total concentration of molybdenum (Mo) and tungsten (W), in wt-%, according to the following formula:

$$\text{Mo} + \text{W}/2 = 3.0 \text{ to } 10.0, \text{ preferably } 4.0 \text{ to } 8.0.$$

[0011] The Cr can be present in 25.0 to 30.0 wt-%.

[0012] The Si can be present in 0.5 to 1.0 wt-%.

[0013] The nickel based-alloy can comprise at least one element of Group 3 of the periodic table, except actinoids, the at least one element being present up to 0.15 wt-%, preferably 0.01 to 0.12; manganese (Mn), the Mn being present up to 0.60 wt-%; iron (Fe), the Fe being present up to 14.8 wt-%; and/or comprising boron (B), the B being present up to 0.01 wt-%.

DETAILED DESCRIPTION OF THE PRESENT INVENTION

[0014] The advantages achieved according to the invention are essentially based on the fact that, at temperatures of up to 1200 °C, intercrystalline creeping in the material is largely prevented due to stable deposits in the intercrystalline regions and an increased mixed crystal hardening is achieved. Additionally, the adhesion of chromium spinel and such layers to the surface is increased, causing an improved high-temperature corrosion resistance of the components.


[0015] The effect and the reciprocal effect of the elements of the nickel-based alloy according to the invention shall be described in greater detail in the following.

[0016] The elements of groups 4, 5, and 6 (except chromium), essentially being titanium (Ti), zirconium (Zr), hafnium (Hf), vanadium (V), niobium (Nb), tantalum (Ta), molybdenum (Mo), and tungsten (W) have a mixed crystal hardening effect and are provided with different activities regarding the non-metal elements carbon and nitrogen. Ta and Nb, for example, form thermally highly stable nitrides, the nitrogen affinity of strong carbide formers Mo and W are low, however. It has been shown that the elements of groups 4, 5, and 6 (except Cr) with a concentration of at least 5 but not more than 20 wt-% in the material are partially embedded in the atomic grid of the matrix in a toughness-increasing manner and partially form nitride and/or carbon nitride dispersion, which increase the intercrystalline stability and, thus, aggravate intercrystalline creeping at temperatures above 1000 °C. Additionally, under such conditions, the dispersion effectively prevents a grain increase.

[0017] Here, the extent of the mixed crystal hardening can be adjusted by the content of carbon and the content of strong carbide formers. For example, if the carbon content of the alloy is low, strong carbide-forming elements are increasingly embedded in the crystal grid of the mixed crystals and brace them.

[0018] A further deciding advantage of the alloy according to the invention is the fact that the above-listed elements, in particular the elements Mo and W, shift the peritectic transformation of the II phase to higher temperatures by substitution of Cr atoms and, thus,

a stabilization of II deposits is caused under operating conditions. A transformation occurring during a rising temperature of approximately 1000 °C



in Ni-Cr-N alloys which correspond to a change in volume of approximately  $1 \times 10^{-3} \%$ , is increased to a temperature of more than 1210°C by a Mo concentration of 4 wt-%, for instance, as may be seen in Table 1. Due to the addition of Mo, for example, no changes in volume occur even at high operating temperatures in a cyclic temperature impact and material wear, resulting in an improvement of the high-temperature corrosion resistance since no cause for peeling of parts of the chromium-spinel surface layer is present.

[0019] Carbon with a content of more than 0.0015 wt-% enhances the formation of nitride and carbon nitride; however, at a content of more than 0.6 wt-% in the alloy, it removes too large an amount of carbide-forming elements, thereby counteracting the matrix hardening. A carbon content of 0.16 to 0.5 wt-% is preferred.

[0020] When, in an advantageous manner, the ratio value of nitrogen to carbon content in the alloy is in the region of 0.5 to 5.5, preferably 1.0 to 4.0, optionally 1.0 to 3.0, particularly effective and stable carbon nitride deposits are formed and an efficient mixed crystal hardening is achieved.

[0021] In order to achieve a II phase as stable as possible during high modification temperatures of the material and, simultaneously, an effective mixed crystal hardening as well, it is advantageous for the nickel-based alloy to be provided with a total concentration of molybdenum and tungsten in wt-% according to the formula

$$\text{Mo} + \text{W}/2 = 3.0 \text{ to } 1.0, \text{ preferably } 4.0 \text{ to } 8.0.$$

[0022] Chromium contents in wt-% of 25 to 30 are preferred. In order to minimize the high-temperature corrosion, it is important for the material to contain at least 0.03 wt-% Al

and at least 0.4 wt-% Si. Contents higher than 3.0 wt-% lead to a disadvantageous deposit characteristic, stress fractures, and the formation of coarse grains and contents higher than 3.0 % of Si worsen the heat forming ability of the alloy.

[0023] The corrosion resistance at high temperatures can be increased when the material is alloyed with elements of group 3 of the periodic table, i.e., scandium (Sc), Yttrium (Y), lanthanum (La), and lanthanides up to a concentration of 0.15 wt-%. Here, contents between 0.01 and 0.12 wt-% are preferred.

[0024] The invention shall be explained in greater detail in the following.

[0025] Nickel-based alloys with a composition according to the invention can be produced by means of pressure metallurgy in which the liquid melt is kept under a constant high pressure until it hardens (e.g., DESU-process) or by powder metallurgy. When PM technology is used, first a metal powder having the desired content of metal elements is produced, this powder is subsequently stacked over the gaseous phase at a raised temperature and subjected to hot isostatic pressing.

[0026] Forming of the casted or sintered blocks usually occurs subsequent to a homogenization of the material at 1250 °C during a forming at 1200 °C. Here, grain sizes of 35 to 80 µm and nickel deposits with a diameter of 1 to 5 µm are produced in the material.

[0027] As previously mentioned, the transformation temperature of the II phase is increased by the presence of elements of group 4, 5, and 6 (except Cr). Table 1 shows the dissolution and formation temperatures that were determined and the compositions of the II phase and those of the mixed crystal for a Ni-Cr-N alloy free of Mo, and for such alloys having a Mo content of 4 to 8 wt-% as well as one having 4 wt-% W. For concentrations of 8 wt-% Mo and 0.7 wt-% N, both temperature values for a transformation  $\pi \leftrightarrow \epsilon$  are greater than 1300°C.

[0028] Here, the II phase is provided with a reduced chromium content of 45 wt-% at a concentration of molybdenum of 11 wt-%. The  $\gamma$  mixed crystal has increased chromium values of 29 wt-% and a content of molybdenum of 6.5 wt-% at a decreased nickel concentration.



Table 1: Influence of the content of molybdenum and tungsten onto the interval of the modification temperature  $\Delta T$  (dilatometer examination) of  $\gamma + Cr_2N$ .

Chemical composition [wt-%]	Ni 30Cr 0.9N	Ni 30Cr 4W 0.7N	Ni 30Cr 4Mo 0.7N	Ni 30Cr 8Mo 0.7N
$\Delta T$ (heating)	1120-1185°C	1160-1180°C	1210-1280°C	>1300°C
$\Delta T$ (cooling)	1180-1195°C	1180-1240°C	1260-1280°C	>1300°C
$\pi$ -phase composition [wt-%]	42 Ni 58 Cr	41 Ni 53 Cr 4.5 W	41 Ni 51 Cr 8 Mo	43 Ni 45 Cr 11 Mo
$\gamma$ -matrix composition [wt%]	77 Ni 23 Cr	68 Ni 26 Cr 5 W	69 Ni 28 Cr 3.5 Mo	65 Ni 29 Cr 6.5 Mo

[0029] Table 2 shows the chemical composition of the alloys according to the invention (alloys 1 through 5) and reference alloys (alloys 6 through 9).

[0030] Table 3 lists the mechanical characteristics of the alloys at 800 °C, at 1000 °C, and at 1100 °C.

[0031] When compared, it is discernible that the 0.2 % yield stress ( $R_{p0.2}$ ) of the material is considerably increased by the alloy technology measures according to the invention and the breaking strain ( $A$ ) each is provided with lower values. In particular, the creep resistance at 1 % stretching of the nickel-based alloy according to the invention is considerably improved in reference to prior art.

[0032] The resistance to high-temperature corrosion is improved in the alloys according to the invention by approximately 16 % (alloy 3 by more than 22 %) in reference to prior art.

Alloys according to the invention: Alloys 1 through 5

Reference alloys: Alloys 6 through 9

Table 2

Alloy	C [%]	Si [%]	Mn [%]	Cr [%]	Mo [%]	Ni [%]	W [%]	Co [%]	N [%]	Al [%]	B [%]	Fe [%]	Nb+Ta [%]	Ce+La [%]
Alloy 1	0.07	0.4	0.1	25.4	-	bal.	8.8	10.3	0.22	0.6	0.001	0.3	-	0.096
Alloy 2	0.05	0.8	0.2	24.2	2.4	bal.	6.3	0.3	0.54	0.5	0.001	5.2	1.4	0.015
Alloy 3	0.25	2.2	0.1	30.1	-	bal.	10.2	0.2	0.28	1.7	0.002	0.2	-	0.138
Alloy 4	0.12	0.5	0.1	26.7	-	bal.	11.3	0.1	0.44	0.3	0.003	0.2	0.8	0.020
Alloy 5	0.08	0.9	0.2	28.3	5.6	bal.	12.5	0.3	0.60	0.2	0.002	0.1	-	0.047
Alloy 6	0.07	0.2	0.1	15.4	-	bal.	-	0.2	-	0.2	0.001	8.8	-	-
Alloy 7	0.03	0.1	0.2	21.6	8.8	bal.	-	0.1	-	0.2	0.002	0.4	3.7	0.003
Alloy 8	0.02	0.8	0.2	31.5	-	bal.	-	0.3	0.48	0.1	0.002	0.1	-	-
Alloy 9	0.10	0.4	0.2	22.1	2.3	bal.	13.7	0.1	-	0.3	0.001	0.2	-	0.008

Table 3

Alloy	Rp0.2 800°C [MPa]	Breaking strain at 800 °C [%]	Rp0.2 1000°C [MPa]	Breaking strain at 1000°C [%]	Rp 1% stretch. 1000°C 500h	Rp0.2 1100°C [MPa]	Breaking strain A at 1100°C [%]	Rp 1% Stretch. 1100°C 500h
Alloy 1	315	21	156	21	20 MPa	71	40	10 MPa
Alloy 2	302	18	130	34	20 MPa	85	49	12 MPa
Alloy 3	391	25	125	25	18 MPa	76	32	10 MPa
Alloy 4	394	19	142	18	22 MPa	82	35	12 MPa
Alloy 5	375	20	152	24	22 MPa	95	42	14 MPa
Alloy 6	102	56	26	115	8 MPa	14	110	4 MPa
Alloy 7	235	96	98	110	13 MPa	46	132	6 MPa
Alloy 8	285	20	80	25	12 MPa	51	48	8 MPa
Alloy 9	270	57	120	83	17 MPa	65	82	8 MPa